

**DeWitt Company, Inc.**  
**WB Pro Black Specifications**

**Typical Properties**

**Test Method**

Basis Weight	ASTM D-3776	3.0 oz/SY
Grab Tensile Strength (lbs/inch)	ASTM D-5034	MD 55 CD 50
Grab Elongation (%)	ASTM D-5034	MD 40 CD 80
Trapezoidal Tear (lbs)	ASTM D-4533	MD 25
Thickness (mils)	ASTM D-1777	24.4
Permittivity (s-1) (hydrophilic only)	ASTM D-4491	0.5
Water Flow Rate (gal/min/ft <sup>2</sup> ) (hydrophilic only)	ASTM D-4491	40
Fiber Content		PP

**Product Benefits**

- Hydro philic treated / allows air and water to pass through.
- Minimizes light penetration to suppress weed growth.
- Fabric is treated to minimize degradation due to UV light exposure.
- Covered (pine straw, pine bark, wood chips, etc...) fabric offers extended use, strong, durable, and resistant to damage from temperature extremes.

Date: 09/01/2011. This data sheet supersedes all previously issued data.

THIS INFORMATION RELATES ONLY TO THE SPECIFIC MATERIAL DESIGNATED AND MAY NOT BE VALID FOR SUCH MATERIAL USED IN COMBINATION WITH ANY OTHER MATERIALS OR IN ANY PROCESS, SUCH INFORMATION IS TO THE BEST OF OUR KNOWLEDGE AND BELIEF, ACCURATE AND RELIABLE AS THE DATE COMPLIED. HOWEVER NO REPRESENTATION, WARRANTY OR GUARANTEE IS MADE AS TO ITS ACCURACY, RELIABILITY OR COMPLETENESS. IT IS THE USER'S RESPONSIBILITY TO SATISFY HIMSELF AS TO THE SUITABILITY AND COMPLETENESS OF SUCH INFORMATION FOR HIS OWN PARTICULAR USE. WE DO NOT ACCEPT LIABILITY FOR ANY LOSS OR DAMAGE THAT MAY OCCUR FROM THE USE OF THIS INFORMATION NOR DO WE OFFER ANY WARRANTY AGAINST PATENT INFRINGEMENT.